

**Amendments to the Claims:**

This listing of claims will replace all prior versions, and listings, of claims in the application:

**Listing of Claims:**

- 5 1.(currently amended) A repairing method for a liquid crystal display panel comprising:

removing a sealant outside a liquid crystal injection area before  
providing a first pressure;

continuously providing ~~[[a]]~~the first pressure to two opposite surfaces  
10 of the liquid crystal display panel;

continuously providing a second pressure to two opposite surfaces of  
the liquid crystal display panel, and removing the sealant in the  
liquid crystal injection area;

continuously providing a third pressure to two opposite surfaces of the  
15 liquid crystal display panel to press liquid crystal out through the  
liquid crystal injection area, and cleaning the pressed-out liquid  
crystal;

sealing the liquid crystal injection area with a fresh sealant and  
continuously providing a fourth pressure to two opposite surfaces  
20 of the liquid crystal display panel; and

curing the fresh sealant and removing the fourth pressure.

2.(original) The repairing method of claim 1, wherein the liquid crystal  
injection area is a liquid crystal injection hole.

25

3.(canceled)

4.(original) The repairing method of claim 1 wherein the liquid crystal injection area is a portion of a sealing area of the liquid crystal display panel, and an auxiliary structure is formed at an edge of the liquid crystal display panel beside the portion of the sealing area.

5

5.(original) The repairing method of claim 4 wherein the auxiliary structure is formed by filling a gap of the liquid crystal display panel with an ultraviolet sensitive material and curing the ultraviolet sensitive material.

10

6.(original) The repairing method of claim 4 wherein the liquid crystal display panel is filled up with the liquid crystal utilizing a one-drop-fill method.

15 7.(original) The repairing method of claim 1 used for repairing an uneven defect on the liquid crystal display panel caused by a gravity issue.

8.(original) The repairing method of claim 1 wherein the step of removing the sealant in the liquid crystal injection area utilizes a laser to burn down  
20 the sealant.

9.(original) The repairing method of claim 1 wherein temperature of the liquid crystal display panel is maintained at 20 to 80°C when providing the first pressure.

25

10.(original) The repairing method of claim 1 wherein temperature of the liquid crystal display panel is maintained at 20 to 80°C when providing the second pressure.

11.(original) The repairing method of claim 1 wherein temperature of the liquid crystal display panel is maintained at 20 to 80°C when providing the third pressure.

5

12.(original) The repairing method of claim 1 wherein the first pressure equals the second pressure.

10 13.(original) The repairing method of claim 1 wherein the second pressure equals the third pressure.

14.(withdrawn) The repairing method of claim 1 wherein the third pressure is larger than the fourth pressure, the fourth pressure is larger than the first pressure, and the first pressure is similar to the second pressure.

15